



## P-YI-250 Homopolymer

### Description:

"Polynar P-YI-250" is a high melt flow homo-polymer polypropylene for the production of CF, BCF and fine denier staple fibers at medium to high spinning speeds and exhibits excellent anti-gasfading properties.

"Polynar P-YI-250" offers a high homogeneity, stable extrusion and excellent processability on both short and long spinning lines. This grade allows a high stretch ratio and gives tough and resilient fibers.

"Polynar P-YI-250" is suitable for nonwoven fabrics for diapers, medical-sanitary applications, surgical garments, geotextiles and wipes. Another typical application is high tenacity continuous filament for straps for backpacks, sport bags, bulk bags and handles for big and safety belts. Continuous filament with medium tenacity is used for upholstery and sportswear and heavy duty clothing.

"Polynar P-YI-250" is also suited for the production of bulked continuous filament for thermo bonding and carpets.

"Polynar P-YI-250" is suitable for food contact.

### Processing Method:

Fiber Extrusion (CF, BCF, staple)

### Features:

High melt flow  
Excellent anti-gasfading properties  
Good processability  
Homopolymer

### Typical Applications:

Nonwoven fabrics for surgical garments, geotextiles, diapers, medical-sanitary applications  
Wipes and tissues  
Straps for backpacks, sport bags, bulk bags and for safety belts  
Upholstery and sportswear  
Bulk continuous filament for carpets  
Nonwoven staple fiber  
Hygiene nonwoven

ISO 9001

OHSAS 18001

ISO 14001



TYPICAL PROPERTIES	VALUE	UNIT	METHOD
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16kg)	25	g/10min	ASTM D1238
Density	0.908	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>			
Flexural Modulus	1498	MPa	ASTM D790
Tensile Strength at Yield	33.86	MPa	ASTM D638
Tensile Elongation at Yield	6.93	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	20.4	J/m	ASTM D256
<b>Thermal</b>			
Vicat softening point (10N)	157	°C	ASTM D1525
H.D.T. (0.46 Mpa)	88.4	°C	ASTM D648

**Head Office:** NO:10 ,Daniali Alley ,Andarzgoo Blvd. Gheyariyeh, TEHRAN-IRAN

TEL:(+9821)22212087 FAX:(+9821)22201946

**Factory:** Azarshahr, Herasati Rd. Next to Tabriz Complex, POLYNAR Petrochemical Co. – TABRIZ-IRAN

TEL:(+98413)4201000 FAX :(+98413)4201001

www.polynar.com

Email:info@polynar.com