



5203

ALCUDIA® 5203 is a high-density polyethylene copolymer of hexene, with middle molecular weight. It is specially designed to make, by blow moulding-extrusion, up to 20 litres containers for liquid detergents and chemicals. This grade contains stabilisers according to the end use of the item in order to reinforce the thermal stability.

Good mechanical properties and good level of both stiffness and environmental stress cracking resistance can be obtained with **ALCUDIA® 5203** due to its molecular weight and density.

MAIN APPLICATIONS

Packaging of liquid detergents and chemical.

PROCESSING

BARREL	HEAD	MELT TEMPERATURE
160 °C - 190 °C	180 °C - 200 °C	180 °C - 200 °C

PROPERTIES

PROPERTIES	UNIT	TYPICAL VALUE	TEST METHOD
A) GENERAL			
- Melt Flow Index (2.16 Kg /190 °C)	g/10 min	0.2	ISO-1133
(21.6 Kg /190 °C)	g/10 min	20.0	ISO-1133
- Density at 23°C	Kg/m ³	950	ISO-1183
- Vicat Softening Point	°C	127	ISO-306
- Hardness, Shore D	°	63	ISO-868
B) MECHANICAL			
- Tensile Strength.	MPa	27	ISO-527
- Elongation at Break.	%	700	ISO-527
- Flexural Modulus	MPa	1100	ISO-178
C) OTHER			
- Environmental Stress Cracking Resistance (ESCR), F ₅₀	h	60	MA-55-3020

ALCUDIA® 5203 complies with FDA standards and European Directives regarding contact with foodstuffs. For more information, please contact our Commercial Delegations.

STORAGE

The polyethylene **ALCUDIA® 5203** should be stored in dry environment at temperatures below 60 °C and protected from UV-light. Improper storage can initiate degradation process can have negative effects in the procesability and the properties of the transformed product.

January 2004

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Head Offices:
P.º de la Castellana, 280
28046 Madrid
Spain
www.repsolypf.com/quimica
e-mail: quimica@repsolypf.com

Customer Service in Europe:
UK, Ireland, Scandinavia:
France, Benelux:
Germany, Austria, Switzerland:
Italy:
Spain:
Portugal:
Other Countries:

Telephone:
+44 20 7581 0300
+33 (1) 46 965 102
+49 (69) 610 93 20
+39 (02) 40 933 92 05
+34 91 348 82 54
800 55 55 55 11
+34 91 348 90 84

e-mail:
sac.uk@repsolypf.com
sac.france@repsolypf.com
sac.deutschland@repsolypf.com
sac.italy@repsolypf.com
sac.quimica@repsolypf.com
sac.portugal@repsolypf.com
sac.quimica@repsolypf.com

TS & Development:
Tel. +34 91 348 8600
Fax: +34 91 530 45 17
e-mail: atdquimica@repsolypf.com
Crtra. Nac. V, km. 18
28931 Móstoles, Madrid
Spain