

Alathon®

M 5350



High Density Polyethylene Injection Molding Grade Melt Index 4.5 Density 0.953

Applications

ALATHON M 5350 is a copolymer with narrow molecular weight distribution. This resin provides high impact strength and stress crack resistance, excellent color, low odor and good processing stability. Typical applications include open head pails, large shipping containers and 55-gallon drum lids.

Regulatory Status

M 5350 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Processing Techniques

Specific recommendations for processing M 5350 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Suggested Start-up Conditions

Extruder Zone	Rear	Center	Front	Nozzle
Cylinder Temperature °F (°C)	450 (232)	470 (243)	475 (246)	475 (246)

Physical Properties

Property	Nominal Value	Units	Test Method
Melt Index	4.5	g/10 min	ASTM D 1238
Density	0.953	g/cc	ASTM D 1505
Spiral Flow ¹	8.4 (21.3)	in (cm)	Equistar
Tensile Strength @ Break ²	3,870 (27)	psi (MPa)	ASTM D 638
Tensile Strength @ Yield ²	4,090 (28)	psi (MPa)	ASTM D 638
Elongation @ Yield ²	7.2	%	ASTM D 638
1% Secant Modulus ³	186,000 (1,280)	psi (MPa)	ASTM D 790B
2% Secant Modulus ³	156,000 (1,080)	psi (MPa)	ASTM D 790B
Vicat Softening Point ⁴	261 (127)	°F (°C)	ASTM D 1525
Hardness, Shore D	68		ASTM D 2240
Heat Deflection Temperature @ 66psi	162 (72)	°F (°C)	ASTM D 648
Low Temperature Brittleness, F ₅₀	<-105 (<-76)	°F (°C)	ASTM D 746

¹ Measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440°F.

² Crosshead speed - 2" min

³ Crosshead speed - 0.5" min

⁴ Data are for control and development work and not intended for use in design or predicting at elevated or sub-ambient temperatures.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at (800) 700-0946.

®Equistar and Alathon are registered trademarks of Equistar Chemicals, LP.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
<http://www.equistarchem.com>
2013/1203

EQUISTAR
A Lyondell Company