

LLDPE LL0209AA
Linear Low Density Polyethylene

1) Product Description:

“LL 0209AA” is a LLDPE copolymer with butene as comonomer which contains anti-oxidant. It is recommended for general purpose applications. It is suitable for blending with conventional LDPE. Film made from pure LL 02090 AA has the following advantages over conventional LDPE: Better sealing, higher puncture resistance Greater drawdown capability Higher tensile strength

Neutralizer: Calcium Stearate Antioxidant: Irganox1010, Irganox168

2) Applications:

Heave duty sacks, agricultural films, liners
Produce bags, stretch film

3) Typical Data

Modulus of elasticity TD	MPa	200	ISO 527
Modulus of elasticity MD	MPa	190	ISO 527
Puncher Resistance			
Coefficient of Friction	--	0.5	ASTM D1894
Thermal Properties			
Melting Point	°C	127	ISO 3146
Property	Unit	Typical Value	Test Method

Modulus of elasticity TD	MPa	200	ISO 527
Modulus of elasticity MD	MPa	190	ISO 527
Puncher Resistance			
Coefficient of Friction	--	0.5	ASTM D1894
Thermal Properties			
Melting Point	°C	127	ISO 3146
Property	Unit	Typical Value	Test Method
Physical			
Melt Flow Rate(MFR) (190 °C/2.16Kg) (190 °C/5Kg) (190 °C/21.6Kg)	g/10min	0.9 ----	ISO 1133
Density	g/cm3	0.920	ISO 1183
Optical Properties			
Haze	%	12	ASTM D1003
Gloss	--	50	ASTM D523
Film Properties			
Impact Strength	gr	150	ASTM D 1709
Tear Strength TD	g/25μ	370	ASTM D1922
Tear Strength MD	g/25μ	145	ASTM D1922
Modulus of elasticity TD	MPa	200	ISO 527

4) Processing Condition:

Recommended melt temperature: 180-225 °C
Film Blowing Machine: Dr.Collin 30M (Extruder) +180/400(Unit)
Zone Temperature: 200 °C
Hopper Temperature: 180 °C Screw speed is set to 50 rpm
The feeder of the extruder is cooled by cooling water CWS/CWR (35-45 °C)
Blow up ratio: 2
Die Diameter: 75 mm
Die Gap: 1.2 mm