

Petrothene®

LH 7350

**High Density Polyethylene
Blow Molding Grade
Melt Index 0.35 Density 0.953**

Applications

The PETROTHENE LH 7350 series of polyethylene resins exhibits an excellent balance of stiffness and environmental stress crack resistance. Typical applications include bottles for bleach, detergents and household chemicals.

Certification

The base resin LH 7350 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information about the use of specific products for specific applications.

Processing Techniques

Specific recommendations for processing LH 7350 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Physical Properties

| Property | Nominal Value | Units | ASTM Test Method |
|--|---------------|-----------|------------------|
| Melt Index | 0.35 | g/10 min | D 1238 |
| Density | 0.953 | g/cc | D 1505 |
| Tensile Strength @ Yield | 3.900 | psi | D 638 |
| Elongation @ Break | 900 | % | D 638 |
| Flexural Modulus | 185,000 | psi | D 790 |
| Tensile Impact | 120 | ft-lb/in. | D 1822 |
| Low Temperature Brittleness, F ₅₀ | <-76 | °C | D 746 |
| Heat Deflection Temperature @ 66 psi | 74 | °C | D 648 |
| Vicat Softening Point | 128 | °C | D 1525 |
| Hardness, Shore D | 66 | | D 2240 |
| Environmental Stress Crack Resistance, F ₅₀ | 50 | hrs | D 1693 |
| | >500 | hrs | D 2561 |

| Product | LH 7350-00 | LH 7350-10 | _____ |
|----------|------------|------------|-------|
| Antistat | None | High | |

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at (800) 700-0946.

®Equistar and Petrothene are registered trademarks of Equistar Chemicals, LP.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
<http://www.equistarchem.com>
6739-10/0201



EQUISTAR