

Alathon

M5370

High Density Polyethylene
Injection Molding Grade

Melt Index 6.9 Density 0.953



Applications Alathon M5370 is a copolymer with a narrow molecular weight distribution. This resin provides high impact strength, excellent color, low odor and good processing stability. Typical applications include open head pails and large shipping containers.

Regulatory Status M5370 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar Product Safety representative for more information.

Processing Techniques Specific recommendations for processing M5370 can only be made when the processing conditions, equipment and end use are known.

Suggested Start-up Conditions	Extruder Zone	Rear	Center	Front	Nozzle
	Cylinder Temperature °F (°C)		450 (232)	470 (243)	475 (246)

Typical Properties

Resin Properties	Nominal Values				Test Method
	English Units	SI	Units		
Melt Index, 190°C, 2.16 kg		6.9	g/10 min	ASTM D1238	
Spiral Flow ¹	8.9 in	22.6	cm	Equistar	
Density		0.953	g/cc	ASTM D1505	
Bulk Density	33-37 lb/ft ³	529-593	kg/m ³	ASTM D1895	
Molded Properties					
Tensile Stress, Yield	4,130 psi	28.5	MPa	ASTM D638*	
Elongation, Yield		9	%	ASTM D638*	
Tensile Stress, Break	2,990 psi	20.6	MPa	ASTM D638*	
Elongation, Break		1,150	%	ASTM D638*	
Flexural Modulus, 1% Secant	189,030 psi	1,300	MPa	ASTM D790**	
Izod Impact, 23 °C	0.73 ft-lbs/in	39	J/m	ASTM D256	
Unnotched Impact, -18°C	No Break	No Break		ASTM D4812	
Vicat Softening Point	261 °F	127	°C	ASTM D1525	
Hardness, Shore D		71		ASTM D2240	
Heat Deflection Temperature, 66 psi ²	162 °F	72	°C	ASTM D648	
Low Temperature Brittleness, F ₅₀ ²	<-105 °F	<-76	°C	ASTM D746	

¹ Measures the number on inches of flow produced when molten resin is injected into a long, spiral channel (0.625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440°F.

² Data are for control and development work and not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

* Conditions: 50 mm/min, Type IV

** Conditions: 12.5 mm/min

These are typical values not to be construed as specification limits.

See page 2 for additional information.

Alathon

M5370

High Density Polyethylene

Injection Molding Grade

Melt Index 6.9 Density 0.953

lyondellbasell

Other
Properties

Thermal Properties

Melting Temperature
Crystallization Temperature

Nominal Values

English Units

SI Units

Test Method

266.5 °F 130.3 °C ASTM D3418
241.7 °F 116.5 °C ASTM D3418

Molded Properties

Flexural Modulus, 2% Secant
Flexural Young's Modulus
Tensile Modulus, 1% Secant
Tensile Young's Modulus

English Units

SI Units

Test Method

157,800 psi 1,090 MPa ASTM D790**
205,100 psi 1,410 MPa ASTM D790**
119,300 psi 823 MPa ASTM D638***
151,300 psi 1,040 MPa ASTM D638***

** Conditions: 12.5 mm/min

*** Conditions: 50 mm/min, Type I

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
Basell Sales & Marketing Company B.V.
Basell Asia Pacific Limited
Basell International Trading FZE
LyondellBasell Australia Pty Ltd

Alathon is a trademark owned or used by LyondellBasell group companies. *Alathon* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or
(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application. U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; and tobacco related products and applications. Additionally, the product(s) may not be used in: (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices; (ii) applications involving permanent implantation into the body; (iii) life-sustaining medical applications; and (iv) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
1221 McKinney Street, Suite 300
Houston, Texas 77010
(888) 777-0232
www.lyondellbasell.com

© LyondellBasell Industries Holdings, B.V. 2014

2105/0514