

HDPE PE100
YUHWA HIDEN P600

Features and Uses

Application	HDPE PE100
Features	PE100, Excellent Creep Resistance, SCG, RCP, Color:Natural
Uses	Gas Pipes, Water Supply and Drain Pipes

Properties

Items	Specification	Unit	Test Method
Melt Index (5kg)	0.21	g/10min.	ASTM D1238
Density	0.95	g/cm ³	ASTM D1505
Water Absorption	<0.01	%	ASTM D570
Tensile Strength at Yield	240	kg/cm ²	ASTM D638
Elongation at Break	>600	%	ASTM D638
Flexural Modulus	9,000	kg/cm ²	ASTM D790
Hardness (Rockwell)	40	R Scale	ASTM D785
Impact Strength (Izod with Notch)	>50	kg _f cm/cm	ASTM D256
Environment Stress Cracking Resistance	>5,000	hr.Cond.B.10%	ASTM D1693
Melting Point	133	°C	ASTM D3418
Softening Point (Vicat)	124	°C	ASTM D1525
Oxidation Induction Time at 200°C	>60	min	ASTM D3895
Heat Deflection Temperature	65	°C	ASTM D648
Brittleness Temperature	<-70	°C	ASTM D746

* Above data are intended to serve as guides only, and are not sales specification limits.

Contact

Division	Team in charge	TEL	FAX	e-mail



YOONAM Bldg 77, Jahamun-ro, Jongno-gu, Seoul, 03035, Rep of Korea Homepage: www.kpic.co.kr
TEL: 82-2-2122-1422 FAX: 82-2-2122-1519 e-mail: master@kpic.co.kr