

**REPSOL
YPF**



**ALCUDIA®
LD POLYETHYLENE**

LDPE ALCUDIA® 2212FA

DESCRIPTION

ALCUDIA® 2212FA is a low density polyethylene grade, produced by high pressure autoclave technology, for blown film applications. This material offers easy processability and good balance of mechanical and optical properties. It contains antioxidant and antiblock additives.

ALCUDIA® 2212FA fulfils the food contact regulations in most countries. For further information or certificates, contact our Customer Service Offices.

APPLICATIONS

- Thin shrink film
- Carrier-bag films
- Pouches refuse sacks
- General packaging film

Recommended melt temperature range from 160 to 190°C.
Processing conditions should be optimised for each production line.

PROPERTIES	TEST METHOD	UNITS	VALUE
General			
Melt Flow Rate (190°C, 2.16kg)	ISO 1133	g/10 min	1.2
Density at 23°C	ISO 1183	kg/m ³	922
Vicat softening temperature (load 10 N)	ISO 306	°C	96
Film (1)			
Dart drop (F ₅₀)	ISO 7765-1	g	140
Tear resistance (Elmendorf) (MD/TD)	ISO 6383-2	cN	400/200
Tensile stress at break (MD/TD)	ISO 527-3	MPa	26/23
Elongation at break (MD/TD)	ISO 527-3	%	300/500
Coefficient of friction (Dynamic)	ISO 8295	-	0.8
Gloss (45°)	ASTM D-2457	%	85
Haze	ASTM D-1003	%	8
Puncture Resistance, force	ASTM D-5748	N	53
Puncture Resistance, energy	ASTM D-5748	J	2

(1) 40 µm thickness film, blow up ratio 2.5:1.

STORAGE

ALCUDIA® 2212FA should be stored in a dry atmosphere paved, drained and not flooded area at temperatures under 60°C and protected from UV radiation. Storage under improper conditions could trigger off degradation processes, negatively influencing processability and the properties of the transformed product.

December 2004

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Head Offices:
P.º de la Castellana, 280
28046 Madrid
Spain
www.repsolypf.com/quimica
e-mail: quimica@repsolypf.com

TS & Development:
Tel.: +34 - 91 348 86 00
Fax.: +34 - 91 530 45 17
e-mail: atdquimica@repsolypf.com
Ctra. de Extremadura, km 18
28931 Móstoles, Madrid
Spain

Customer Service in Europe:
UK, Ireland, Scandinavia: Tel.: 44 - 20 7581 0300
France, Benelux: Tel.: 33 (0) 146 965 102
Germany, Austria, Switzerland: Tel.: 49 - 69 610 93 20
Italy: Tel.: 39 - 02 40 933 92 05
Spain: Tel.: 34 - 91 348 82 54
Portugal: Tel.: 800 55 55 55 11
Other Countries: Tel.: 34 - 91 348 90 84

e-mail:
sac.uk@repsolypf.com
sac.france@repsolypf.com
sac.deutschland@repsolypf.com
sac.italy@repsolypf.com
sac.quimica@repsolypf.com
sac.portugal@repsolypf.com
sac.quimica@repsolypf.com