



## Jampilen RP340R

Random Copolymer



**Description:** 

"Jampilen RP340R" is a nucleated polypropylene random copolymer with high fluidity and outstanding transparency and gloss and is designed for injection molding applications.

"Jampilen RP340R" is the material of choice for applications where transparency is a primary requirement. This grade is also suitable for injection stretch blow molded containers and bottles. This product combines good see through clarity and excellent moisture barrier properties with hot fillability. Therefore, "Jampilen RP340R" offers an effective alternative for PET and PVC for the packaging of non-oxygen sensitive products such as confectionary, herbs, toiletries and cosmetics.

**Processing Method:** Injection molding

Injection stretch blow molding

**Features:** High melt flow

Excellent transparency

Excellent gloss Random copolymer

**Typical Applications:** Household containers, housewares

> Packaging for food, cosmetics and pharmaceutical products Clear tubs and pots for ice cream, yoghurt and other desserts

Medical sector such as syringes, test tubes and vials

Lids, caps and closures CD and DVD boxes

Injection stretch blow molded containers and bottles

Sports, leisure and toys

**Approval:** Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	25	g/10min	<b>ASTM D1238</b>
Density	0.9	g/cm <sup>3</sup>	ASTM D1505
Mechanical			_
Flexural Modulus	1050	MPa	ASTM D790
Tensile Strength at Yield	28	MPa	ASTM D638
Tensile Elongation at Yield	12	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	65	J/m	ASTM D256
Rockwell Hardness	94	R Scale	ASTM D785
Thermal			
Vicat softening point (10N)	127	$^{\mathrm{o}}\mathrm{C}$	<b>ASTM D1525</b>
H.D.T. (0.46 Mpa)	83	$^{\circ}\mathrm{C}$	ASTM D648
Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012
Optical			_
Haze (1 mm)	22	%	ASTM D1003
Gloss	73		ASTM D2457

<sup>4</sup>th Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran.

Tel: +9821-84286, Fax: +9821-88879811

Email: info@jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.