



(1)	Description:
$\overline{\mathbf{C}}$	
	Processing N
\searrow	Features:
()	
\bigcirc	Typical App
Ľ	
()	
	TYPICAL PI
	Physical Melt Flow Rat
\bigcirc	Density
\bigcirc	Mechanical Tensile Modu
0	Tensile Streng
	Tensile Elong
	Tensile Elong
	Charpy impac 23°C
	<u>0°C</u>
	Optical Gloss (60°)

scription:	"Jampilen EP440G" is a nucleated heterophasic copolymer especially developed for extrusion applications. "Jampilen EP440G" exhibits high stiffness, very high impact properties at room and sub-zero temperatures, good dimensional stability and excellent creep and deforming resistance. The main applications of "Jampilen EP440G" are thermoforming, corrugated board and extrusion blow molding.		
ocessing Method:			
U	Thermoforming		
	Extrusion blow molding		
atures:			
	Very high impact resistance		
	High stiffness		
	Good dimensional stability		
	Excellent creep and deforming resistance		
	Heterophasic copolymer		
pical Applications:			
	Crates		
	Panels & Profiles		
	Corrugated Sheet		
	Conduit pipes and fittings for electrical distribution and cable protection		
	Blow molded bottles and containers		

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	1.3	g/10min	ISO 1133
Density	0.9	g/cm ³	ISO 1183
Mechanical			
Tensile Modulus	1450	MPa	ISO 527-1, -2
Tensile Strength at Yield	27	MPa	ISO 527-1, -2
Tensile Elongation at Break	>50	%	ISO 527-1, -2
Tensile Elongation at Yield	8	%	ISO 527-1, -2
Charpy impact strength (Notch A)			ISO 179
23°C	40	kJ/m ²	
0°C	9	kJ/m ²	
Optical			
Gloss (60°)	65		DIN 67530

4th Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran. Tel: +9821-84286, Fax: +9821-88879811 Email: info@jppc.ir www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.