

January, 2008

KOPELEN JM-365

PP BLOCK COPOLYMER

General Information

Description

JM-365 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-365 shows better impact resistance than normal block copolymer and has good physical property balance.

Applications

- ◆ Industrial supplies
- ◆ Automotive compound base resin

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	26	g/10min		
Density	ASTM D792	0.9	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	250	kgf/cm ²	25	MPa
Tensile Strain (Break)	ASTM D638	>100	%	>100	%
Flexural Modulus	ASTM D790	13,000	kgf/cm ²	1,270	MPa
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	9.0	kgf-cm/cm	88	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	4.5	kgf-cm/cm	44	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	103	℃		
Additional Properties					
Flammability	UL94	-			

NOTE

ISO 9001, 14001, /ITS 16949

¹ Physical Properties : these are not to be construed as specifications

www.hpc.co.kr