

## Reliance Industries Limited

## $P \hspace{0.1cm} O \hspace{0.1cm} L \hspace{0.1cm} Y \hspace{0.1cm} P \hspace{0.1cm} R \hspace{0.1cm} O \hspace{0.1cm} P \hspace{0.1cm} Y \hspace{0.1cm} L \hspace{0.1cm} E \hspace{0.1cm} N \hspace{0.1cm} E$

REPOL H030SG HOMOPOLYMER

## Product description & applications

REPOL Polypropylene H030SG is manufactured using Unipol PP process which combines the production efficiency of gas phase fluidized bed reactor technology with the high activity stereospecific catalyst system.

Repol H030SG is recommended for **Raffia Tapes** used in making woven fabrics for sacking, carpet backing, industrial packaging and geotextile applications.

Typical properties of Repol H030SG are as follows:

## Features:

Repol H030SG is designed to provide:

- High tenacity in tapes
- Consistent processability
- Low "water carryover"
- Good colour and processing stability

Property	ASTM	Unit	Typical Value*
	Test Method		
Melt flow index, (230°C / 2.16kg)	D 1238	g/10 min	3.0
Tensile strength at yield (50mm/min)	D 638 <sup>\$</sup>	MPa	35
Elongation at yield (50mm/min)	D 638 <sup>\$</sup>	%	10
Flexural modulus (1% secant )	D 790A <sup>\$</sup>	MPa	1650
Notched Izod Impact strength (23°C)	D 256 <sup>\$</sup>	J/m	40
Heat deflection temp. (455 kPa)	D 648	°C	104

\$: ASTM D638 Type I specimen injection moulded and tested in accordance with ASTM D4101

04-05

Repol H030SG meets the requirements stipulated in IS 10910 on "Specification for Polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS-10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

REPOL is the registered trademark for Polypropylene from Reliance Industries Limited

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or local.

The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorized agent, as the information and/or data is subject to change based on the research and development work undertaken by the company.

<sup>\*</sup> Typical values with injection moulded specimens, not to be taken as specification