

LOTTE CHEMICAL

January, 2013

HOPELEN Y-130

PP HOMO POLYMER

General Information

Description

Y-130 is a propylene homopolymer designed for stretched products such as flat yarn It is a low flow rate resin with a broad molecular weight distribution. It complies with FDA regulation.

Applications

Flat yarns for woven bags, tape and rope

Physical Properties ¹						
Physical	Test Method		Nominal Values			
Melt Flow Index	ASTM D1238	4.0	g/10min			
Density	ASTM D792	0.90	g/cm ³			
Mechanical						
Tensile Stress (Yield)	ASTM D638	350	kgf/cm ²	34	MPa	
Tensile Strain (Break)	ASTM D638	>500	%			
Flexural Modulus	ASTM D790	16,000	kgf/cm ²	1,560	MPa	
Rockwell Hardness	ASTM D785	103	R			
Impact						
Notched Izod Impact Strength (23 °C)	ASTM D256	4.0	kgf-cm/cm	39	J/m	
Thermal						
Heat Deflection Temperature (4.6kgf/cm²)	ASTM D648	116	${\cal C}$			
VICAT Softening Point	ASTM D1525	151	${\cal C}$			

NOTE	ISO 9001, 14001, /TS 16949			
¹ Physical Properties : these are not to be construed as specifications				

www.lottechem.com